

PORON[®] 4701-V0-M Medium

DATA SHEET

PROPERTY	TEST METHOD	PORON [®] V-0
FOAM PROPERTIES		
DENSITY, kg / m ³ (lb. / ft ³)	ASTM D 3574 Test A	400 (25)
Tolerance, %		±10
COMPRESSION FORCE DEFLECTION, kPa (psi)	Modified ASTM D 3574: PTP-0033 at 25% deflection	41 - 110 (6 - 16)
COMPRESSION SET, %	ASTM D 3574 Test D, 23°C	5
COMPRESSION SET, %	ASTM D 3574 Test D, 70°C	10
TENSILE, kPa (psi)	ASTM D 3574 Test E	Typical Value: 580 (84)
ELONGATION, %	ASTM D 3574 Test E	Typical Value: 111
HARDNESS, pts	SHORE O	Typical Value: 24
STANDARD COLOR (CODE)		Smoke Gray (107)
TEMPERATURE RANGE		
RECOMMENDED CONSTANT USE, Max °C (Max °F)	SAE J-2236 for 1008 hours	90 (194)
RECOMMENDED INTERMITTENT USE, Max °C (Max °F)	SAE J-2236 for 168 hours	121 (250)
BRITTLENESS TEMPERATURE BY IMPACT, °C (°F)	ASTM D 746-13	-20 (-4)
COLD FLEXIBILITY	MIL-P-12420 D at -40°C (-40°F)	PASS
FLAMMABILITY		
FLAME RESISTANCE	UL94 V-0	PASS
	UL94 HF-1	PASS
	FMVSS 302	PASS
ENVIRONMENTAL / OFFGASSING		
ROHS 2.0 TESTING SGS REPORT		PASS
REACH COMPLIANCE		PASS
WATER ABSORPTION, Typical %	AMS 3568B (High Humidity)	<2
	ASTM D570 (Immersion Testing)	25
ELECTRICAL AND THERMAL		
DIELECTRIC STRENGTH, kV/mm	ASTM D 149	1.5
DIELECTRIC CONSTANT, K (DK)	ASTM D 150 at RT	~4.0 at 20 Hz (~2.6 at 1x10 ⁶ Hz)
VOLUME RESISTIVITY (DRY AND 90% RH)	Rogers Method based on ASTM D257	Surface Resistivity ~ 10 ¹¹ Ohm/sq
		Volume Resistivity ~ 10 ¹¹ Ohm-cm
THERMAL CONDUCTIVITY, W/m-K	ASTM 1530 at RT	0.292
COEFFICIENT OF THERMAL EXPANSION, mm/mm C	TMA at 5 C/min heating rate	0.00031
HEAT CAPACITY, J/cm ³ K	ISO/DIS 22007-2.2 (Hot Disk)	0.59
	THICKNESS MM (IN)	PORON[®] V-0
	5 (0.197)	
	6 (0.236)	

Standard Product

- Additional technical information is available.
- All PORON Test Procedures are available for view. Please contact Mason Grogan Industrial.

Mason Grogan Industrial | 1300 859 960 or +61 (02) 9748 3838 | salesmg@grogangroup.com | www.grogangroup.com

The information contained in this Data Sheet is intended to assist you in designing with Rogers' PORON Urethane. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Urethane for each application. The Rogers logo, The world runs better with Rogers, and PORON are licensed trademarks of Rogers Corporation. ©2013, 2014 Rogers Corporation, All rights reserved. Printed in U.S.A. 0314-PDF. Publication #17-277

The world runs better with Rogers.®