

# PORON® ThinStik™ Foams Preliminary Data Sheet

## FAMILY OF SELF-ADHESIVE SOLUTIONS

### PRODUCT OFFERINGS

<b>ThinStik ShockSeal™</b> PORON 79-09021 + Supported Adhesive	<b>ThinStik 92-09</b> PORON 92-09020 + Supported Adhesive	<b>ThinStik 92-12</b> PORON 92-12020 + Supported Adhesive	<b>ThinStik Soft Seal</b> PORON 15-06021 + Supported Adhesive	<b>ThinStik Soft Seal</b> PORON 15-06030 + Supported Adhesive
--	---	---	---	---

### TYPICAL PROPERTIES

	Property	Method	Detail	Unit	Value				
Urethane	<b>Description</b>				79TS1-09021	92TS1-09020	92TS1-12020	15TS1-06021	15TS1-06030
	<b>Color (code)</b>				Black (04)	Black (04)	Black (04)	Gray (90)	Gray (90)
	<b>Density</b>	ASTM D 3574-95	Test A	lb/ft³ (kg/m³)	9 (144) ± 1 (16)	9 (144) ± 1 (16)	12 (192) ± 2 (32)	6.5 (104) ± 1 (16)	6.5 (104) ± 1 (16)
	<b>Tolerance</b>								
	<b>Compression Force Deflection</b>	Strain rate = 0.2" / minute	@ 25% Deflection	typical psi (kPa)	1.06 (7.31)	0.80 (5.52)	1.63 (11.2)	0.46 (3.2)	0.31 (2.15)
<b>Compression Set</b>	ASTM D 3574-95	Test D @ 73°F (23°C) Test D @ 158°F (70°C)	% max	5 10	5 10	5 10	5 10	5 10	

	Property	Method	Detail	Unit	Value
Supported Adhesive	<b>Peel Adhesion</b>	ASTM D1000 180° Peel	<b>20 min @ RT / 72 @ hrs RT</b> to Stainless Steel to Polypropylene to Polycarbonate to ABS to Acrylic	oz/in (N/25mm)	28.9 (8.0) / 32.7 (9.1) 28.0 (7.8) / 28.7 (8.0) 30.7 (8.5) / 36.2 (10.1) 29.4 (8.2) / 34.8 (9.7) 29.5 (8.2) / 34.6 (9.6)
	<b>Release Adhesion</b>	ASTM D1000 180° Peel	Room Temp 96 hr @ 66°C/ 80% RH	gram / in	9.4 10.6
	<b>Tack</b>	ASTM D 2979 (1 sec dwell)	Room Temp 96 hr @ 66°C/ 80% RH	grams	424 411
	<b>Tensile</b>	ASTM D 882	Room Temp MD / CMD 96 hr @ 66°C/ 80% RH	lb (kg)	12.0 (5.4) / 9.1 (4.1) 11.4 (5.1) / 11.0 (5.0)
	<b>Elongation</b>	ASTM D 882	Room Temp MD / CMD 96 hr @ 66°C/ 80% RH	%	78 / 32 74 / 66
	<b>Shelf Life</b>		from date of manufacture	months	12

### Adhesive Information

PORON® ThinStik™ materials utilize an acrylic pressure sensitive adhesive manufactured to Rogers' specifications. This adhesive provides reliable bonding to a wide variety of substrates, exhibits high quality optical clarity, withstands a wide range of temperatures and is resistant to chemical exposure.

### Storage Information

PORON ThinStik materials have a shelf life of 12 months from the date of manufacture when stored at room temperature. Storage in the original packaging, located in a dry, cool environment is recommended.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foam Materials for each application. The Rogers logo, The world runs better with Rogers., ThinStik, ShockSeal and PORON are licensed trademarks of Rogers Corporation. © 2011 Rogers Corporation, All rights reserved. Printed in U.S.A., 0411-PDF, Publication #17-218

PRODUCT CONSTRUCTION

**PORON ThinStik ShockSeal 79-09 Foam (79TS1-09021)**

Material	Description	Thickness		Tolerance	
		mm	mil	mm	mil
<i>Urethane Foam</i>	PORON ShockSeal Series	0.48	19	± 0.1	± 4.0
<i>Supported Adhesive</i>	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
<b>Total Construction*</b>	<b>Foam, PET, Adhesive</b>	0.52	20.5	± 0.1	± 4.0

**PORON ThinStik 92-09 Foam (92TS1-09020)**

Material	Description	Thickness		Tolerance	
		mm	mil	mm	mil
<i>Urethane Foam</i>	PORON 92-09 Series	0.46	18	± 0.1	± 4.0
<i>Supported Adhesive</i>	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
<b>Total Construction*</b>	<b>Foam, PET, Adhesive</b>	0.50	19.5	± 0.1	± 4.0

**PORON ThinStik 92-12 Foam (92TS1-12020)**

Material	Description	Thickness		Tolerance	
		mm	mil	mm	mil
<i>Urethane Foam</i>	PORON 92-12 Series	0.46	18	± 0.08	± 3.0
<i>Supported Adhesive</i>	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
<b>Total Construction*</b>	<b>Foam, PET, Adhesive</b>	0.50	19.5	± 0.08	± 3.0

**PORON ThinStik Soft Seal Foam (15TS1-06021)**

Material	Description	Thickness		Tolerance	
		mm	mil	mm	mil
<i>Urethane Foam</i>	PORON Soft Seal Series	0.48	19	± 0.1	± 4.0
<i>Supported Adhesive</i>	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
<b>Total Construction*</b>	<b>Foam, PET, Adhesive</b>	0.52	20.5	± 0.1	± 4.0

**PORON ThinStik Soft Seal Foam (15TS1-06030)**

Material	Description	Thickness		Tolerance	
		mm	mil	mm	mil
<i>Urethane Foam</i>	PORON Soft Seal Series	0.72	28.5	± 0.1	± 4.0
<i>Supported Adhesive</i>	PET and Adhesive	0.038	1.5	+ 0.005/- 0.01	+ 0.2/- 0.4
<b>Total Construction*</b>	<b>Foam, PET, Adhesive</b>	0.76	30	± 0.1	± 4.0

\*Note: A liner comes attached to the foam that is removed prior to use. The liner thickness is not included above.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foam Materials for each application. The Rogers logo, The world runs better with Rogers., ThinStik, ShockSeal and PORON are licensed trademarks of Rogers Corporation. © 2011 Rogers Corporation, All rights reserved. Printed in U.S.A., 0411-PDF, Publication #17-218